



PAVESAND™

PAVE JOINT SAND

MEETS NZS3116: 2002 CONCRETE SEGMENTAL & FLAGSTONE PAVING / KILN DRIED

AVAILABLE SIZE:
20KG

YIELD per 20kg bag

Paver recommended gap width 2-4mm. This table should be used as a guide only.

Holland 50 6m ²	Holland 80 3.75m ²	Walkway 50 9.4m ²	Forum 18m ²	Piazza 12m ²	Flagstone 20.2m ²	Chancery 24m ²
-------------------------------	----------------------------------	---------------------------------	---------------------------	----------------------------	---------------------------------	------------------------------

Dricon® PaveSand™ is specially designed for filling joints between paving. It consists of a uniformly blended mixture of graded sands, to allow flexible filling of vertical joints. It forms a flexible joint allowing slight movement of the pavers.

COMPRESSIVE STRENGTH

Not applicable.

WATER CONTENT
Not applicable

PAVER PREPARATION

Ensure the pavers have had an initial vibrating plate compaction of 2 passes to bed them in to the underlying bedding sand. For pedestrian and private driveways the plate compactor should have the following minimum characteristics; 60-120kg static weight and 10-24Kn centrifugal force. The pavers must also be dry.

SPREADING

On completion of laying the pavers, PaveSand™ should be spread evenly over the surface and swept into all the joints using a stiff broom.

Sand flows more freely into the paving joints when the paving is dry.

FILLING

Fill joints to the top of the pavers.

COMPACTION

Compact for at least 2 passes with a plate compactor.

RE-APPLY, RE-SWEEP. RE-COMPACT

Re-apply PaveSand™ to top up the joints, sweep and re-compact.

Repeat until PaveSand™ is sitting, compacted, just below the top of the pavers.

INSPECTION

Dricon® recommend regular inspection of the completed paving project over the first few weeks to ensure the standard joints are maintained.



DANGER

- Causes skin irritation
- May cause respiratory irritation
- Causes serious eye damage
- If medical advice is needed, have product container or packaging at hand

PREVENTION

- Only use outdoors or in a well-ventilated area
- Avoid breathing dust
- Wear protective clothing – safety goggles and a P2 dust mask must be worn
- Contaminated clothing should not be allowed out of the workplace

RESPONSE

IF ON SKIN: Wash with plenty of soap and water. Take off contaminated cloth and wash before reuse. If skin irritation or rash occurs, get medical advice/attention.

IF INHALED: Move to fresh air and keep resting in a position comfortable for breathing.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if worn and easy to do. Continue to rinse.

Immediately call the NATIONAL POISON CENTRE 0800 764 766 or doctor/physician.

GENERAL INFORMATION

If only part of the bag is required, mix the entire contents of the bag together first in a dry state, return the unwanted portion to the bag or alternatively a dry sealed container, then follow the instructions.

All mortars and concrete products may exhibit a temporary 'whitening', otherwise known as efflorescence which neither affects strength nor durability.



DOWNLOAD OUR FREE APP & MAKE SURE YOU ARE USING THE RIGHT PRODUCT FOR YOUR JOB